

PP DOOR THICKNESS AND SIZE

Thickness (mm)	Size (ft.)
30	6.5X2.5
30	6.5X3.5
30	7X3.5
32	6.5X2.5
32	6.5X3.5
32	6.5X3.25
32	7X3
32	7X3.5



The Premium Plus Door is designed to be an ideal solution for your personalized and commercial spaces. Crafted from high-quality eucalyptus hardwood fibers, this door offers a blend of durability and elegance.

Our pre-engineered doors offer an environmental friendly and economical solution for your interior needs. Unlike traditional wood doors are crafted with sustainability in mind, reducing the demand for natural wood resources and providing a more eco-conscious choice for your spaces.

These doors are available in two sturdy options — 30mm and 32mm thickness — Premium Plus Door combines functionality with sophistication.



CENTURYPROWUD®

Century Plyboards (India) Limited

Engineered Panel Products Division

Sales & Marketing Office: Tower B - 8th Floor, Vatika Mindscape,

Sector 27D, Faridabad, Haryana - 121003.

Ph.: 7042399909 | Email: prowud@centuryply.com

www.centuryprohud.com | Follow us on: @centuryprohud



10

YEAR WARRANTY

INTRODUCING **LOWER EMISSION** PREMIUM PLUS DOOR

PRE-ENGINEERED FOR TOUGHNESS



Termite Resistance



High Density



Water Resistant



Fungal Resistance



Borer Resistance

*Terms & conditions apply.

DOORS TECHNICAL SPECIFICATIONS

Properties (Physical & Machanical)	Specs as per IS 12406 : 2021, Gr 1	Century Premium Plus Door (32 mm)	Century Premium Plus Door (30 mm)
Thickness (mm)	± 0.3 mm	32.26	30.09
Length (mm)	± 3 mm/mtr.	-	-
Width (mm)	± 3 mm/mtr.	-	-
Density (Kg/CBM)	600-900	825	810
Surface Density (Kg/CBM)	NA	1085/1105	1062/1066
Moisture Content %	5-10	5.74	5.71
Water Absorption %			
2 hrs	6	2.58	2.23
24 hrs	12+	7.18	8.29
Linear Expansion			
a. Due to general absorption (after 24 hrs soaking) %			
Thickness	7	3.98	3.22
Length	0.3	-	-
Width	0.3	-	-
b. Due to surface absorption (in thickness) after 02 hrs soaking	4	-	-
Internal Bond N/sq mm	0.55	1.13	1.08
After accelerated water resistance	0.1	0.061	0.06
Screw Withdrawal strength (N)			
Face	1250	3494	3256
Edge (>12mm)	800	2633	2812
Modulus of Rupture N/sq mm			
Avg	17	37.96	32.26
Individual	15	36.96	31.54
Modulus of Elasticity N/sq mm			
Avg	2100	3573	2976
Individual	1900	3486	2889
Formaldehyde Content, for oven dry board (mg/100g)	E1: Fc ≤ 8, E2:8< Fc ≤ 30	26.12	26.58

10 REASONS WHY YOU SHOULD USE PREMIUM PLUS DOOR

Premium Plus Door	Claims
High Density	Yes
Tougher Than Plywood	Yes
Water Resistant	Yes
Maximum Screw Holding Capacity	Yes
Calibrated Panel	Yes

Premium Plus Door	Claims
Routable Substrate	Yes
Borer Resistance	Yes
Termite Resistance	Yes
Fungal Resistance	Yes
No Splinters/Chipping	Yes



HIGH DENSITY



TOUGHER THAN PLYWOOD



TERMITE RESISTANCE



WATER RESISTANT



BORER RESISTANCE



NO SPLINTERS/ CHIPPING



ROUTABLE SUBSTRATE



MAXIMUM SCREW HOLDING CAPACITY



FUNGAL RESISTANCE



CALIBRATED PANEL